

TECHNICAL DATA

BASIS	POLYURETHAN FOAM
TYPE	POLYESTER (ESTER)
CELLULAR STRUCTURE	OPEN
COLOUR	GRAY
DENSITY	25/30 KG/m ³
TEMPERATURE RANGE CONSTANT	- 30° C + 100° C
ELONGATION AT BREAK	170%
TENSILE STRENGTH	1,2 KG/cm ² (120 kPa)
COMPRESSION DEFLECTION	AT 40% - 0,040 KG/cm ² (4 kPa)
COMPRESSION SET 50% (22 hours at 70°C)	20%
FLAME TEST ACCORDING TO STANDARD	HF-1 (UL-94)
FLAME TEST ACCORDING TO STANDARD	FMVSS 302
CELLS	nr.13 x cm
THERMAL CONDUCTIVITY	0,032 Kcal/Mh 20°

The above given information should be considered as a guide but cannot regarded as an engagement from our side.